

REMARKS

Entry of this amendment and reconsideration of this application, as amended, are respectfully requested.

Claims 8-10 and 13 were rejected under 35 U.S.C. §103(a) over the combination of Hansen and Clifford. Claims 11-12 were rejected under 35 U.S.C. §103(a) over Hansen, Clifford and Bittner. Claim 14 was rejected under 35 U.S.C. §103(a) over Hansen, Clifford and Oci. Claims 15 and 16 were rejected under 35 U.S.C. §103(a) over Hansen, Clifford and Shaw. Applicants respectfully traverse.

Applicants reiterate that advantages of the presently claimed invention include, generally, improved process time and improved gassing properties. Treatment time for a part to be coated is only about half of the time if nitroguanidine is added. Typically, e.g., 18 min – 12 min of pickling time and 6 min of coating time were required. With nitroguanidine about 9 min – 6 min pickling time and 3 min coating time are required. The pickling process is conducted with an acidic solution: If there is a beginning coating the pickling and gassing effect (generation of H and H₂) can destroy the coating again. During the strong pickling in the pickling time, the hydrogen gas is going out which is well seen by gas bubbling (gassing time). Only after the pickling period, when the solution is not as acidic, is the phosphate coating is developed. Since there is a decreased time and volume of hydrogen gas with the method of the present invention, the risk of making steel more brittle with hydrogen gas (gassing) is lowered too.

Furthermore, it is believed that the Rule 132 Declaration of Ralf Schneider submitted herewith provides the Examiner with answers raised with respect to his previously filed Declaration; and so it is believed to overcome any of the 35 U.S.C. §103(a) rejections raised based all or in part on the combination of Hansen and Clifford.

Additionally, with respect to the rejection of claims 11-12 over Hansen, Clifford and Bittner, please note that Bittner only relates to coating a galvanized or alloy galvanized side, while the present claims relate to the coating of iron or steel surfaces. Furthermore Bittner

relates to zinc or zinc manganese phosphating, which is different from the claimed manganese phosphating process.

Furthermore, Applicants invite the Examiner to reconsider all of the Declarations of Ralf Schneider and Klaus-Dieter Nittel which is self-explanatory and support the foregoing.

In view of the foregoing, withdrawal of all rejections is believed to be proper.

Allowance is respectfully requested.

The Commissioner is hereby authorized to charge any deficiency in the fees filed to our Deposit Account No. 50-0624 under Order No. NY-CHEMMT-206.1-US.

Dated: October 30, 2008

Respectfully submitted,

By 

James R. Crawford

Registration No.: 39,155
FULBRIGHT & JAWORSKI L.L.P.
666 Fifth Avenue
New York, New York 10103
(212) 318-3000
(212) 318-3400 (Fax)
Attorneys for Applicant